

Serial No.: 10/632,176
Art Unit: 2811

BEST AVAILABLE COPY

In the Claims

The following is a copy of Applicant's claims that identifies language being added with underlining (" ") and language being deleted with strikethrough (""), as is applicable:

1-17. (Canceled)

18. (Previously presented) A method for fabricating micro-electro-mechanical system (MEMS) capacitive resonators, the method comprising:

forming trenches in a semiconductor-on-insulator substrate;

conformally coating sidewalls of the trenches with an oxide;

filling the coated trenches with polysilicon, wherein electrodes are derived from the polysilicon;

forming release openings and removing the polysilicon and at least a portion of the semiconductor-on-silicon substrate; and

removing the conformally coated oxide and an oxide of the semiconductor-on-insulator substrate, wherein a capacitive gap is formed, wherein a resonating element of one of the capacitive resonators is released.

19. (Previously presented) The method of claim 18, further including:

growing and patterning an insulator oxide, wherein the insulator oxide provides isolation between the semiconductor-on-insulator substrate and wire-bonding pads;

depositing and patterning nitride, wherein the nitride provides protection for the insulator oxide disposed on the pads;

growing and removing a surface treatment oxide, wherein the surface treatment oxide

Serial No.: 10/632,176
Art Unit: 2811

enables the reduction of the roughness of sidewalls of the resonating element;
depositing polysilicon to form the wirebonding pads for drive and sense electrodes;
metallizing the pads; and
wherein removing the polysilicon includes patterning the polysilicon inside the
trenches

20. (Currently amended) The method of claim 18, wherein the forming release openings comprises anisotropically etching to an oxide layer of the semiconductor-on-insulator substrate, such that the undercut of the resonating element is facilitated.

21. (Original) The method of claim 18, wherein the filling includes one of filling the trenches with doped LPCVD polysilicon such that the electrodes are formed vertically and depositing and patterning doped LPCVD polysilicon.

22. (Original) The method of claim 18, wherein the forming trenches includes one of deep reactive ion etching and regular reactive ion etching to an oxide layer of the semiconductor-on-insulator substrate.

23. (Original) The method of claim 18, wherein the conformally coating includes depositing a LPCVD high-temperature oxide of approximately less than 100 nanometers.

24. (Original) The method of claim 18, wherein the conformally coating is scalable to correspond to a desired thickness of a lateral gap spacing for the capacitive resonator.

Serial No.: 10/632,176

Art Unit: 2811

25. (Original) The method of claim 18, wherein the removing comprises an anisotropic plasma etching such that at least a portion of the oxide remains on sidewalls of the resonating element.

26. (Original) The method of claim 18, wherein the releasing comprises exposing the semiconductor-on-insulator substrate to a solution comprising HF:H₂O to release the resonating element from a handle layer and the electrodes.

27. (Original) The method of claim 18, wherein the forming trenches includes etching high-aspect ratio trenches.

28. (Original) The method of claim 18, wherein the removing includes forming a gap between the resonating element and the polysilicon in a self-aligned manner.

29-35. (Canceled)

36. (Previously presented) The method of claim 18, wherein the removing is performed to form a plurality of capacitive gaps and release a plurality of resonating elements, each of the plurality of resonating elements electrically isolated from each other.

Serial No.: 10/632,176

Art Unit: 2811

37. (Previously presented) A method for fabricating micro-electro-mechanical system (MEMS) capacitive resonators, the method comprising:

forming trenches in a semiconductor-on-insulator substrate;

conformally coating the sidewalls of the trenches with an oxide;

filling the coated trenches with polysilicon, wherein electrodes are derived from the polysilicon;

forming release openings and removing the polysilicon and at least a portion of the semiconductor-on-silicon substrate without isotropic etching of the polysilicon or semiconductor portion of the semiconductor-on-silicon substrate; and

removing the conformally coated oxide and an oxide of the semiconductor-on-insulator substrate, wherein a capacitive gap is formed, wherein a resonating element of one of the capacitive resonators is released.

38. (Previously presented) The method of claim 37, further including:

growing and patterning an insulator oxide, wherein the insulator oxide provides isolation between the semiconductor-on-insulator substrate and wire-bonding pads;

depositing and patterning nitride, wherein the nitride provides protection for the insulator oxide disposed on the pads;

growing and removing a surface treatment oxide, wherein the surface treatment oxide enables the reduction of the roughness of sidewalls of the resonating element;

depositing polysilicon to form the wirebonding pads for drive and sense electrodes;

metallizing the pads; and

wherein removing the polysilicon includes patterning the polysilicon inside the trenches.

Serial No.: 10/632,176
Art Unit: 2811

39. (Currently amended) The method of claim 37, wherein the forming release openings comprises anisotropically etching to an oxide layer of the semiconductor-on-insulator substrate such that the undercut of the resonating element is facilitated.
40. (Previously presented) The method of claim 37, wherein the filling includes one of filling the trenches with doped LPCVD polysilicon such that the electrodes are formed vertically and depositing and patterning doped LPCVD polysilicon.
41. (Previously presented) The method of claim 37, wherein the forming trenches includes one of deep reactive ion etching and regular reactive ion etching to an oxide layer of the semiconductor-on-insulator substrate.
42. (Previously presented) The method of claim 37, wherein the conformally coating includes depositing a LPCVD high-temperature oxide of approximately less than 100 nanometers.
43. (Previously presented) The method of claim 37, wherein the conformally coating is scalable to correspond to a desired thickness of a lateral gap spacing for the capacitive resonator.
44. (Previously presented) The method of claim 37, wherein the removing comprises an anisotropic plasma etching such that at least a portion of the oxide remains on sidewalls of the resonating element.

Serial No.: 10/632,176

Art Unit: 2811

45. (Previously presented) The method of claim 37, wherein the releasing comprises exposing the semiconductor-on-insulator substrate to a solution comprising HF:H₂O to release the resonating element from a handle layer and the electrodes.

46. (Previously presented) The method of claim 37, wherein the forming trenches includes etching high-aspect ratio trenches.

47. (Previously presented) The method of claim 37, further including conformally coating surfaces of the semiconductor-on-insulator substrate with the oxide associated with conformal coating.

48. (Previously presented) A method for fabricating micro-electro-mechanical system (MEMS) capacitive resonators having sharply defined boundaries, the method consisting of:
growing or depositing an oxide layer on a semiconductor-on-insulator substrate and patterning the oxide to the shape of the resonators;

forming trenches in the semiconductor-on-insulator substrate by using the oxide layer as a mask;

conformally coating sidewalls of the trenches with an oxide;

filling the coated trenches with polysilicon, wherein electrodes are derived from the polysilicon;

forming release openings and removing the polysilicon and at least a portion of the semiconductor-on-silicon substrate without isotropic etching of the polysilicon or semiconductor portion of the semiconductor-on-silicon substrate; and

forming a resonating element having sharply defined boundaries of one of the capacitive resonators by removing the conformally coated oxide and an oxide of the

Serial No.: 10/632,176
Art Unit: 2811

semiconductor-on-insulator substrate, wherein a capacitive gap is formed, wherein the resonating element is released.

49. (Previously presented) A method for fabricating micro-electro-mechanical system (MEMS) capacitive resonators having a height-to-width ratio of less than one, the method comprising:

forming trenches in a semiconductor-on-insulator substrate;

conformally coating sidewalls of the trenches with an oxide;

filling the coated trenches with polysilicon, wherein electrodes are derived from the polysilicon;

forming release openings and removing the polysilicon and at least a portion of the semiconductor-on-silicon substrate without isotropic etching of the polysilicon or semiconductor portion of the semiconductor-on-silicon substrate; and

forming a resonating element having a height-to-width ratio of less than one of the capacitive resonators by removing the conformally coated oxide and an oxide of the semiconductor-on-insulator substrate, wherein a capacitive gap is formed, wherein the resonating element is released.

50. (Previously presented) The method of claim 49, further including:

growing and patterning an insulator oxide, wherein the insulator oxide provides isolation between the semiconductor-on-insulator substrate and wire-bonding pads;

depositing and patterning nitride, wherein the nitride provides protection for the insulator oxide disposed on the pads;

growing and removing a surface treatment oxide, wherein the surface treatment oxide enables the reduction of the roughness of sidewalls of the resonating element;

Serial No.: 10/632,176
Art Unit: 2811

depositing polysilicon to form the wirebonding pads for drive and sense electrodes;
metallizing the pads; and
wherein removing the polysilicon includes patterning the polysilicon inside the
trenches.

51. (Previously presented) The method of claim 49, wherein the forming release openings comprises anisotropically etching to an oxide layer of the semiconductor-on-insulator substrate, such that the undercut of the resonating element is facilitated.

52. (Previously presented) The method of claim 49, wherein the filling includes one of filling the trenches with doped LPCVD polysilicon such that the electrodes are formed vertically and depositing and patterning doped LPCVD polysilicon.

53. (Previously presented) The method of claim 49, wherein the forming trenches includes one of deep reactive ion etching and regular reactive ion etching to an oxide layer of the semiconductor-on-insulator substrate.

54. (Previously presented) The method of claim 49, wherein the conformally coating includes depositing a LPCVD high-temperature oxide of approximately less than 100 nanometers.

55. (Previously presented) The method of claim 49, wherein the conformally coating is scalable to correspond to a desired thickness of a lateral gap spacing for the capacitive resonator.

Serial No.: 10/632,176

Art Unit: 2811

56. (Previously presented) The method of claim 49, wherein the removing comprises an anisotropic plasma etching such that at least a portion of the oxide remains on sidewalls of the resonating element.
57. (Previously presented) The method of claim 49, wherein the releasing comprises exposing the semiconductor-on-insulator substrate to a solution comprising HF:H₂O to release the resonating element from a handle layer and the electrodes.
58. (Previously presented) the method of claim 49, further comprising conformally coating surfaces of the semiconductor-on-insulator substrate with the oxide associated with conformal coating.
59. (Previously presented) The method of claim 18, further including conformally coating surfaces of the semiconductor-on-insulator substrate with the oxide associated with conformal coating.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.